

AD-A219 424

SECURITY CLASSIFICATION OF THIS PAGE

2

DTIC REPORT DOCUMENTATION PAGE				
1a. REPORT SECURITY CLASSIFICATION Unclassified		1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY MAR 16 1990		3. DISTRIBUTION/AVAILABILITY OF REPORT Unclassified/Unlimited		
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE		4. PERFORMING ORGANIZATION REPORT NUMBER ONR Technical Report #21		
5. MONITORING ORGANIZATION REPORT NUMBER(S)		6a. NAME OF PERFORMING ORGANIZATION Corrosion Research Center		
6b. OFFICE SYMBOL (If applicable)		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research, Resident Rep.		
7b. ADDRESS (City, State, and ZIP Code) University of Minnesota Minneapolis, MN 55455		8a. ADDRESS (City, State, and ZIP Code) 800 North Quincy Street Arlington, VA 22217-5000		
8b. OFFICE SYMBOL (If applicable) Code 1113		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER Contract No. N00014-88-K-0360		
10. SOURCE OF FUNDING NUMBERS		PROGRAM ELEMENT NO.		
PROJECT NO.		TASK NO.		
WORK UNIT ACCESSION NO.		11. TITLE (Include Security Classification) XPS Studies of Doped Polypyrrole Films		
12. PERSONAL AUTHOR(S) Liliana Atanasoska, Katsuhiko Naoi and William H. Smyrl				
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM 1/1/89 TO 1/25/90		14. DATE OF REPORT (Year, Month, Day) January 25, 1990
15. PAGE COUNT				
16. SUPPLEMENTARY NOTATION 177th Meeting of the Electrochemical Society, Extended Abstracts, May 1990				
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP		
		XPS, conducting polymers, polypyrrole		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) X-ray photoelectron spectroscopy was used to characterize electropolymerized polypyrrole films doped with monomeric ( $\text{ClO}_4^-$ ) and polymeric, poly(vinylsulfonate) and poly(4-styrenesulfonate) anions. Electrostatic interaction between the polymer and the incorporated anions involves the whole pyrrole ring rather than specific nitrogen heteroatom sites only. $\text{ClO}_4^-$ counterions have a planar configuration and are incorporated parallel to the planar rings. On the other hand, the large polymeric counterions are more randomly distributed around polymeric chain. After sputtering, counterions were found to be randomly distributed along the polymer chain. The analysis of the XPS data which leads to these conclusions will be discussed. (P)				
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS		21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Boone B. Owens		22b. TELEPHONE (Include Area Code) (612) 625-1332		22c. OFFICE SYMBOL

# 75-Word Abstract Form

Extended Abstract must be submitted with the 75-Word Abstract by December 1, 1989

## Montreal, Quebec, Canada—May 6-11, 1990

Submit to: The Electrochemical Society, Inc.  
10 South Main Street, Pennington, NJ 08534-2896  
With a copy to the Organizer

Abstract No. ....  
(to be assigned by the Society)

Schedule for The Chemistry and Physics of Composite Media.....  
(Title of Symposium)

Sponsored by Energy Technology/Corrosion.....  
(Division/Group)

Title of paper XPS Studies of Doped Polypyrrole Films.....

Authors (Underline name of author presenting paper.) Ljiljana Atanasoska, Katsuhiko Naoi and.....  
William H. Smyrl.....

Business affiliation and address Corrosion Research Center, Department of Chemical Engineering  
and Materials Science, University of Minnesota.....

Minneapolis, MN.....55455.....(612) 625-5827.....  
(State or Country) (ZIP Code) (Telephone No.)

(Type abstract in this area—double-spaced.)

X-ray photoelectron spectroscopy was used to characterize electropolymerized polypyrrole films doped with monomeric( $\text{ClO}_4^-$ ) and polymeric, poly(vinylsulfonate) and poly(4-styrenesulfonate) anions. Electrostatic interaction between the polymer and the incorporated anions involves the whole pyrrole ring rather than specific nitrogen heteroatom sites only.  $\text{ClO}_4^-$  counterions have a planar configuration and are incorporated parallel to the planar rings. On the other hand, the large polymeric counterions are more randomly distributed around polymeric chain. After sputtering, counterions were found to be randomly distributed along the polymer chain. The analysis of the XPS data which leads to these conclusions will be discussed.

Do you require any audiovisual equipment?

- ☐ 35 mm (2 x 2 in.) slide projector
- ☐ Overhead projector
- ☐ Other equipment at author's expense and subject to availability

Has the information in this abstract been presented verbally, submitted for publication, or published?

☐ Yes ☐ No

If the answer is yes, please provide the reference (except in the case of invited review presentations).

Is a full length paper on this work to be submitted for Society Journal publication? ☐ Yes ☐ No

## XPS Studies of Doped Polypyrrole Films

Ljiljana Atanasoska, Katsuhiko Naoi and William H. Smyrl

Corrosion Research Center,  
Department of Chemical Engineering and Materials Science,  
University of Minnesota, Minneapolis, Minnesota 55455, U.S.A.

### Introduction

Electropolymerized conducting polymers have been studied because of their wide range of useful applications in electronic devices such as batteries, capacitors, ion sensors and electrochromic devices.<sup>1</sup> Electropolymerization has proved to be one of the best means to produce good quality electroactive conducting polymer films with doped anions under in-situ conditions. However, the structure of such conducting polymers has yet not been clarified in spite of the substantial effort at characterization with various surface analysis techniques.<sup>2</sup>

In the present paper, the authors will describe the microscopic structure of polypyrrole films which were electrochemically grown with monomeric and/or polymeric anions. The rigorous ex-situ XPS analysis enabled us to interpret the chemical and structural environment within the polymer with interactions by dopant anions which were incorporated into the polymer matrix during electropolymerization.

### Results and Discussion

The C 1s, O 1s, N 1s and Cl 2p core level spectra shown in Figs. 1a-1d are typical of the PPY+ClO<sub>4</sub><sup>-</sup> films formed in the potential range from 0.4-1.2 V(vs. Ag/AgNO<sub>3</sub>(acetonitrile)).

The major feature in the C 1s photoemission is centered at about 284.5 eV (Fig. 1a). The carbon peak is asymmetric and skewed towards high binding energies. As seen from Fig. 1a, the C 1s spectra can be decomposed into four lines (labeled 1-4) by varying only their relative intensities. Peak 2 is assigned to the  $\alpha$  carbons and is always more intense than peak 1 due to  $\beta$  carbons.

The ideal pyrrole monomer unit contains two  $\alpha$  and two  $\beta$  carbon atoms and the difference in intensity between the  $\alpha$  and  $\beta$  carbon lines has been explained by the presence of the hydrocarbon contamination.<sup>3</sup> However, hydrocarbon contamination would add to the intensity of  $\beta$  carbon photoemission which is more hydrocarbon-like than  $\alpha$  carbon, and would be a random function of the experimental conditions. The latter is contrary to experimental results. We suggest instead that the C 1s lineshape originates from *inequivalent pyrrole monomer units* in terms of electrostatic interactions with perchlorate anions. The photoemission of the pyrrole rings modified by electrostatic interaction with nearly anions would be shifted towards higher binding energies.

The N 1s spectra of the polypyrroles polymerized at different potentials indicate clearly the existence of two inequivalent nitrogen heteroatoms (Fig. 1c). The shoulder shifted by 1.6 eV with respect to the main nitrogen feature is attributed to those nitrogens in pyrrole rings which have strong electrostatic interaction with nearly anions.

The presence of Cl<sup>-</sup> species is always observed in the Cl 2p region of as received polymer samples (Fig. 1d). After sputtering, the high energy shoulder in the N 1s region disappeared indicating that the N heteroatoms in the sputtered films are not modified the electrostatic interaction. This finding can be explained by a sputter-disturbance of a doped polymer structure. The lineshape of the C 1s photoemission was not changed upon sputtering.

The C 1s and N 1s lineshape analysis indicate that the entire pyrrole ring unit is modified by the electrostatic interaction with anion. We propose that an ordered type of doped polypyrrole structure is formed in which the flat ClO<sub>4</sub><sup>-</sup> anion is placed parallel to the planar pyrrole ring. The negatively charged ClO<sub>4</sub><sup>-</sup> ion is approximately the same size as the monomer unit and produces an electric field at the ring site which affects all 4 carbon and 1 nitrogen atoms in its vicinity by making them more positive. Any specific electrostatic bonding at the nitrogen heteroatom site would result in a considerably larger shift of the shoulder of the N 1s core level than the one observed in our measurements. A disorder-type

of doped polypyrrole structure develops upon sputtering or by doping the polypyrrole with the large size anions like poly(4-styrenesulfonate). The relative position and angle between the ring and the planar anion vary randomly for the sputter-disordered PPY+ClO<sub>4</sub><sup>-</sup> films. The large anions of complex three dimensional configuration can not form closely packed parallel ring-anion pairs which are suitable for the specific ring site electrostatic interaction. The anions are randomly distributed along the polymer chains and the specific anion-ring electrostatic interaction is converted into a uniform charge extraction from the polymer backbone. The C 1s lineshape is preserved in the random type of anion distribution, which indicates that the carbon atoms are affected more strongly than nitrogen heteroatom by such uniform charge extraction.







Fig.1 Core level photoelectron peaks for as-grown polypyrrole films(PPYClO<sub>4</sub><sup>+</sup>): (a) C 1s; (b) O 1s; (c) N 1s; (d) Cl 2p.

#### References

1. K.Naoi and T.Osaka, *J. Electrochem. Soc.*, **134**, 2479 (1987).
2. T. Osaka, K. Naoi and S. Ogano, *J. Electrochem. Soc.*, **135**, 1071 (1988); G.B. Street, S. E. Lindsey, A. I. Nazzaal and K. J. Wynne, *Mol. Cryst. Liq. Cryst.*, **118**, 137 (1985); J. Bargon, S. Mohmand and R. J. Waltman, *IBM Res. Delp.*, **27**, 330 (1983).
3. P. Pfluger and G. B. Street, *J. Chem. Phys.*, **80**, 544 (1984).

Accession For	
NTIS CRANI	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Dist	Availability Codes
A-1	